

Sika Noleek™

Powder based waterproofing admixture for mortar and concrete

Construction

Product Description	Sika Noleek™ is an integral waterproofing admixture in powder form for concrete and mortar
Uses	Sika Noleek™ is recommended for use in structural concrete, particularly for the following: <ul style="list-style-type: none">■ Slope Roof Slab■ Flat Roof Slab■ Beams■ Columns■ Slabs Also used in: <ul style="list-style-type: none">■ Internal and external plaster of buildings etc.■ Repair and renovation
Characteristics / Advantages	<ul style="list-style-type: none">■ Compatible with all varieties of Portland Cement including Slag Cement.■ Easy to use■ Effective pore filler to prevent water seepage■ Easy compaction resulting in denser concrete■ Reduced shrinkage, better finish■ Rebound loss is low■ No added chloride- does not attack reinforcement■ Supplied in consumer friendly pack
Tests	
Approvals/Standard	IS 2645 : 1975
Product Data	
Form	
Appearance / Colour	White fine powder
Packaging	1kg
Storage	
Storage Conditions / Shelf-Life	Best before 6months from date of production if stored properly in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.



Technical Data

Chemical Base	Talc
Bulk Density	0.4-0.6 gm/cc

System Information

Application Details

Consumption / Dosage	1kg per 50 kg bag of cement (2% by weight of cement)
----------------------	--

Application Instruction

Dispensing	For Concrete:
	<ul style="list-style-type: none"> ■ Add Sika Noleek™ while dry mixing cement, sand and aggregates ■ Add water gradually directly to the dry mix to get the required consistency ■ Mix the entire quantity for approx. 3 minutes to achieve homogeneous mix ■ Recommended water for concrete is 23 - 25 litres per 50 kg bag of cement ■ Pour the mixture on a tray and use as per requirement and lay the concrete ■ Cure as per normal procedure by ponding/ curing compound (Sika® Antisol EWP / Antisol® A)
	For Mortar:
	<ul style="list-style-type: none"> ■ Add Sika Noleek™ while dry mixing cement and sand ■ Add water gradually directly to the dry mix to get the required consistency ■ Mix the entire quantity for approx. 3 minutes to achieve homogeneous mix ■ Recommended water for mortar is 28 - 30 litres per 50 kg bag of cement ■ Use as per requirement and lay the mortar ■ Cure as per normal procedure by sprinkling with water/ curing compound (Antisol® EWP / Antisol® A)

Cleaning of Tools	Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.
-------------------	---

Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
------------	--

Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
-------------------------------	---

Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.
-------------	--



Registered office: Sika India Pvt. Ltd. Phone +91 33 2447 2448/2449
 Commercial Complex II Telefax +91 33 2396 8688
 620, Diamond Harbour Road ind.sika.com
 Kolkata, 700 034, India info.india@in.sika.com